

MANN BAMBOO FIBER WARE CO.,LTD

NO. 12629 FANHUA AVENUE, ECONOMIC DEVELOPMENT ZONE, HEFEI, ANHUI, CHINA


The following sample(s) was/were submitted and identified on behalf of the clients as : BAMBOO FIBRE TABLEWARE

SGS Job No. : HFHL2103001572CW  
 Date of Sample Received : 05 JAN 2021  
 Testing Period : 05 JAN 2021 - 11 JAN 2021  
 Test Requested : Selected test(s) as requested by client.  
 Test Method : Please refer to next page(s).  
 Test Results : Please refer to next page(s).

Result Summary :

Test Requested	Conclusion
German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 30 and 31 with amendments, European Commission Regulation (EU) No 10/2011 with amendments, Commission Regulation (EU) No 284/2011 of 22 March 2011 and BfR recommendation-Specific migration of formaldehyde	PASS

Signed for and on behalf of  
 SGS-CSTC Standards Technical Services Co., Ltd. Ningbo Branch



Iris Xiao  
 Approved Signatory

scan to see the report



SGS-CSTC Standards Technical Services Co., Ltd.  
 Ningbo Branch Chemical Laboratory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)

15/F West of Building 4, Lingyun Industry Park, No.1177 Lingyun Road, Ningbo National Hi-Tech Zone, Ningbo, Zhejiang, China 315040 t E&E (86-574)89070249 www.sgsgroup.com.cn  
 中国·浙江·宁波市国家高新区凌云路1177号凌云产业园4号楼西1-5层 邮编: 315040 t HL (86-574)89070271 t ML (86-574)89070242 e sgs.china@sgs.com

Test Results :

Test Part Description :

Specimen No	SGS Sample ID	Description	Material (claimed by the client)
SN1	HFB21-005262.001	Beige melamine&bamboo fibre cup	MELAMINE+BAMBO O FIBRE

Remarks :

- (1) mg/dm<sup>2</sup> = milligram per square decimeter
- (2) mg/kg = milligram per kilogram
- (3) °C= degree Celsius
- (4) < = less than
- (5) MDL = Method Detection Limit
- (6) ND = Not Detected ( < MDL)

German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 30 and 31 with amendments, European Commission Regulation (EU) No 10/2011 with amendments, Commission Regulation (EU) No 284/2011 of 22 March 2011 and BfR recommendation-Specific migration of formaldehyde

Test Method : With reference to EN13130-1:2004, analysis was performed by UV-Vis.

Sample 001

Simulant Used : 3% Acetic acid (W/V) aqueous solution

Test Condition : 70.0 °C 2.0 hr(s)


<u>Test Item(s)</u>	<u>Max. Permissible Limit</u>	<u>Unit</u>	<u>MDL</u>	<u>Test result</u>
Migration times	-	-	-	3rd
Area/volume	-	dm <sup>2</sup> /kg	-	6.0
Max extractable Formaldehyde	15	mg/kg	0.1	3.6

Notes :

- (1) Test condition was referred to EU JRC guidelines EUR 24815 EN 2011, in support of Commission Regulation (EU) No 284/2011 of 22 March 2011.
- (2) The test is performed in triplicate as per EU JRC guidelines EUR 24815 EN 2011, in support of Commission Regulation (EU) No 284/2011 of 22 March 2011. The highest value among 3 trial results is reported.



Sample photo:



SGS authenticate the photo on original report only

\*\*\* End of Report \*\*\*

